

## BOLIDTOP® 700 PT

			Conc. (%)	Temp. (°C)	Value				Conc. (%)	Temp. (°C)	Value
<b>OILS AND GREASES</b>						<b>ALKALIES</b>					
linseed oil	100	20	++	caustic soda	10	20	++	caustic soda	50	20	++
olive oil	100	20	++	ammonia	10	20	++	ammonia	25	20	++
castor oil	100	20	++	caustic potash	10	20	++	caustic potash	50	20	++
vegetable oils	100	20	++	caustic potash	50	20	++	calcium hydroxide	25	20	++
animal fats	100	20	++	<b>SALTS</b>							
skydrol 500	100	20	++	sodium chloride	saturated	20	++	sodium chloride	saturated	40	++
diesel oil	100	20	++	ammonium chloride	saturated	20	++	barium chloride	saturated	20	++
motor oil	100	20	++	barium chloride	saturated	20	++	calcium sulphate	saturated	20	++
transmission oil	100	20	++	calcium sulphate	saturated	20	++	nickel chloride	saturated	20	++
petrol	100	20	++	nickel chloride	saturated	20	++	nickel sulphate	saturated	20	++
<b>FRUIT AND VEGETABLE JUICES</b>						<b>SOLVENTS</b>					
vegetable juice	100	20	++	acetone - short spill exposure	100	20	-	acetone - long spill exposure	100	20	-
vegetable juice	100	40	++	toluene	100	20	+	toluene	100	20	+
apple juice	100	20	++	xylene	100	20	+	xylene	100	20	+
apple juice	100	40	++	styrene	100	20	+	styrene	100	20	+
lemon juice	100	20	++	methyl ethyl keton (MEK)	100	20	+	methyl ethyl keton (MEK)	100	20	-
lemon juice	100	40	++	methylene chloride	100	20	-	methylene chloride	100	20	-
orange juice	100	20	++	chloroform	100	20	-	chloroform	100	20	-
orange juice	100	40	++	ethanol	30	20	++	ethanol	100	20	+
grape juice	100	20	++	ethanol	100	20	+	methanol	100	20	+
grape juice	100	40	++	methanol	100	20	+	n-butanol	100	20	+
wine	100	20	++	n-butanol	100	20	++	benzene	100	20	++
wine	100	40	++	benzene	100	20	++	cyclohexan	100	20	++
<b>INORGANIC ACIDS</b>						<b>VARIOUS</b>					
hydrochloric acid	20	20	++	isopropyl alcohol	100	20	+	isopropyl alcohol	100	20	-
hydrochloric acid	20	30	+	phenol	100	20	-	phenol	100	20	-
hydrochloric acid	37	20	+	ethyleneperchloride	100	20	++	ethyleneperchloride	100	20	+
sulphuric acid	10	20	++	carbon tetrachloride	100	20	+	carbon tetrachloride	100	20	+
sulphuric acid	10	30	+	ethylene trichloride	100	20	+	ethylene trichloride	100	20	+
sulphuric acid	20	20	+	turpentine	100	20	++	turpentine	100	20	++
sulphuric acid concentrated	98	20	-	petroleum	100	20	++	petroleum	100	20	++
phosphoric acid	10	20	+	parraffin	100	20	++	parraffin	100	20	++
phosphoric acid	10	30	-	butyl acetate	100	20	+	butyl acetate	100	20	+
phosphoric acid	40	20	-	heptane	100	20	++	heptane	100	20	++
phosphoric acid concentrated	85	20	-	n-methylpyrrolidone	100	20	-	n-methylpyrrolidone	100	20	-
nitric acid	10	20	+	<b>glucose</b> saturated 20 ++							
nitric acid	10	30	-	<b>beer</b> 100 20 ++							
nitric acid	30	20	-	<b>beer</b> 100 40 ++							
nitric acid	30	30	-	<b>soap solution</b> saturated 20 ++							
nitric acid concentrated	70	20	-	<b>mercury</b> 100 20 ++							
chromic acid	10	20	++	<b>hydrogen peroxide</b> 10 20 ++							
chromic acid	20	20	++	<b>distilled water</b> 100 20 ++							
chromic acid	40	20	++	<b>distilled water</b> 100 40 ++							
<b>ORGANIC ACIDS</b>						<b>seawater</b> 100 20 ++					
acetic acid	10	20	+	<b>seawater</b> 100 40 ++							
acetic acid	30	20	-								
citric acid	10	20	++								
citric acid	30	20	++								
lactic acid	10	20	+								
lactic acid	30	20	+								
formic acid	10	20	-								
oxalic acid	10	20	+								

++ = resistant  
+ = limited resistant

- = not resistant  
0 = unknown

IP.21.03.16

Bolidt Kunststofopassing B.V.  
Nijverheidsweg 37  
P.O.Box 131  
3340 AC Hendrik-Ido-Ambacht  
The Netherlands