

BOLIDTOP® 500

CHARACTERIZATION

This flow-applied floor finish system has excellent flow properties and a well-sealed surface without pores. This smooth and comfortable industrial flooring is suitable for medium (forklift) traffic. A silicon decor mixture is optional. The system is seamless, durable, impermeable to fluids, low maintenance and applied on site by own specialists.

PROPERTIES

Bolidtop 500 is an approx. 2 mm thick flooring system based on two-component hard synthetic resins. Bolidtop 500 has a smooth surface structure due to its excellent flow properties. Its seamless character, adhesion and durability characteristic make this flooring well suited for medium traffic such as forklift trucks and heavy pallet trucks.

Bolidtop 500 is resistant to most common chemicals. A broad range of colours gives the architect numerous possibilities to ensure that the flooring harmonises with the character of the building.

Bolidtop 500 can be cleaned with commonly available cleaning products, but preferably with the products that are marketed by Bolidt.

APPLICATION

The flooring system is very suitable for kitchen areas, metal production, storage spaces, charging stations, bund lining, printing offices, canteens, (practical) laboratories, workshops and rinsing areas. This synthetic flooring is often applied in new buildings and renovation projects.

COLOURS

You can find the colours that Bolidtop 500 is available in through the online service at <http://colors.bolidt.com>. On request and on revised terms, it is possible to deviate from this colour range.

COMPOSITION

The polymers that are used in this system are tolerant, low viscous and low odour. They are based on solvent-free and waterborne synthetic resins. Bolidt Kunststoftoepassing develops and produces the products in accordance with ISO 9001:2000.

INSTALLATION

Bolidtop 500 is processed in liquid form and has to be applied by experts. That is why Bolidtop 500 can only be installed by the application specialists who work with Bolidt or its certified partners.

BASE SURFACE

The most suitable bases for Bolidtop 500 are sand-cement screed, concrete and anhydrite. These need to be in good condition: stable, dry, clean and degreased. A detailed description of these and other base surfaces can be requested separately.

SETTING

Bolidtop 500 can be walked on after 24 hours and can be mechanically loaded after 48 hours. Full chemical setting is attained after 7 days at room temperature.

Bolidt Kunststoftoepassing B.V.
Nijverheidsweg 37
P.O.Box 131
3340 AC Hendrik-Ido-Ambacht
The Netherlands