

BOLIDTOP® 700

CHARACTERIZATION

This solid and aesthetically sound floor finish system is characterized by its high impact and shock resistance. The mechanically compacted flooring has a terrazzo look and can withstand very heavy loads. The slightly antiskid surface contributes to a safe working environment. The system is seamless, durable, impermeable to fluids, low maintenance and applied on site by own specialists.

PROPERTIES

Bolidtop 700 is an approx. 5 mm thick, mechanically compacted and seamless synthetic floor finish based on two-component low-viscous synthetic resins that are low odour. Bolidtop 700 has a terrazzo look. Due to the high shock, impact and pressure resistance, Bolidtop 700 is ideal for heavy forklift traffic and pallet transport. Bolidtop 700 is scratch proof and durable.

Bolidtop 700 is resistant to most common chemicals. Bolidtop 700 is available in a large number of terrazzo colours.

Bolidtop 700 can be cleaned with commonly available cleaning products, but preferably with the products that are marketed by Bolidt.

APPLICATION

The flooring system is very suitable for storage spaces, printing offices and production areas. This synthetic flooring is often applied in new buildings and renovation projects.

COLOURS

You can find the colours that Bolidtop 700 is available in through the online service at <http://colors.bolidt.com>. On request and on revised terms, it is possible to deviate from this colour range.

COMPOSITION

The polymers that are used in this system are tolerant, low viscous and low odour. They are based on solvent-free and waterborne synthetic resins. Bolidt Kunststoftoepassing develops and produces the products in accordance with ISO 9001:2000.

INSTALLATION

Bolidtop 700 is processed in liquid form and has to be applied by experts. That is why Bolidtop 700 can only be installed by the application specialists who work with Bolidt or its certified partners.

BASE SURFACE

The most suitable bases for Bolidtop 700 are sand-cement screed, concrete and anhydrite. These need to be in good condition: stable, dry, clean and degreased. A detailed description of these and other base surfaces can be requested separately.

SETTING

Bolidtop 700 can be walked on after 24 hours and can be mechanically loaded after 48 hours. Full chemical setting is attained after 7 days at room temperature.

Bolidt Kunststoftoepassing B.V.
Nijverheidsweg 37
P.O.Box 131
3340 AC Hendrik-Ido-Ambacht
The Netherlands