

BOLIDTOP® 700 EM

CHARACTERIZATION

This reinforced floor finish system is characterized by its high impact and shock resistance. The mechanically compacted flooring has a terrazzo look and can withstand heavy loads, even when the underlying surface is not optimal. The slightly antiskid surface contributes to a safe working environment. The system is seamless, durable, impermeable to fluids, low maintenance and applied on site by own specialists.

PROPERTIES

Bolidtop 700 EM is an approx. 9 mm thick, mechanically compacted and seamless floor finish based on two-component low-viscous synthetic resins that are low odour. The system is reinforced with expanded metal and has a terrazzo look. Due to the high shock, impact and pressure resistance, Bolidtop 700 EM is ideal for heavy forklift traffic and pallet transport. De Bolidtop 700 EM is scratch proof and durable.

Bolidtop 700 EM is resistant to most common chemicals. Bolidtop 700 EM is available in a large number of terrazzo colours.

Bolidtop 700 EM can be cleaned with commonly available cleaning products, but preferably with the products that are marketed by Bolidt.

APPLICATION

The flooring system is very suitable for storage spaces, printing offices and production areas. This synthetic flooring is often applied in new buildings and renovation projects.

COLOURS

You can find the colours that Bolidtop 700 EM is available in through the online service at <http://colors.bolidt.com>. On request and on revised terms, it is possible to deviate from this colour range.

COMPOSITION

The polymers that are used in this system are tolerant, low viscous and low odour. They are based on solvent-free and waterborne synthetic resins. Bolidt Kunststofopassing develops and produces the products in accordance with ISO 9001:2000.

INSTALLATION

Bolidtop 700 EM is processed in liquid form and has to be applied by experts. That is why Bolidtop 700 EM can only be installed by the application specialists who work with Bolidt or its certified partners.

BASE SURFACE

The most suitable bases for Bolidtop 700 EM are sand-cement screed, concrete and anhydrite. These need to be in good condition: stable, dry, clean and degreased. A detailed description of these and other base surfaces can be requested separately.

SETTING

Bolidtop 700 EM can be walked on after 24 hours and can be mechanically loaded after 48 hours. Full chemical setting is attained after 7 days at room temperature.

Bolidt Kunststofopassing B.V.
Nijverheidsweg 37
P.O.Box 131
3340 AC Hendrik-Ido-Ambacht
The Netherlands