

BOLIDTOP® 910 CHR

CHARACTERIZATION

This industrial floor finish system is extremely resistant to chemicals. Especially the harmful effects of (in)organic acids, salts, oils and fats are minimal. This flooring can withstand heavy traffic. The antiskid surface is suitable for use in wet conditions. The system is seamless, durable, impermeable to fluids, low maintenance and applied on site by own specialists.

PROPERTIES

Bolidtop 910 CHR is an approx. 3.5 mm thick floor finish system based on three-component highly chemical-resistant synthetic resins. Due to the antiskid surface, Bolidtop 910 CHR is very suitable for use in wet and oily conditions. Bolidtop 910 CHR is scratch proof and durable. The system is suitable for forklift traffic.

Bolidtop 910 CHR is highly resistant to most common chemicals. Especially its resistance to (in)organic acids is excellent.

Bolidtop 910 CHR can be cleaned with commonly available cleaning products, but preferably with the products that are marketed by Bolidt.

APPLICATION

The flooring system is very suitable for distilleries, charging stations, bund lining and filling rooms. This synthetic flooring is often applied in new buildings and renovation projects.

COLOURS

You can find the colours that Bolidtop 910 CHR is available in through the online service at <http://colors.bolidt.com>. On request and on revised terms, it is possible to deviate from this colour range.

COMPOSITION

The polymers that are used in this system are tolerant, low viscous and low odour. They are based on solvent-free and waterborne synthetic resins. Bolidt Kunststofopassing develops and produces the products in accordance with ISO 9001:2000.

INSTALLATION

Bolidtop 910 CHR is processed in liquid form and has to be applied by experts. That is why Bolidtop 910 CHR can only be installed by the application specialists who work with Bolidt or its certified partners.

BASE SURFACE

The most suitable bases for Bolidtop 910 CHR are sand-cement screed, concrete and anhydrite. These need to be in good condition: stable, dry, clean and degreased. A detailed description of these and other base surfaces can be requested separately.

SETTING

Bolidtop 910 CHR can be walked on after 36 hours and can be mechanically loaded after 72 hours. Full chemical setting is attained after 28 days at room temperature.

Bolidt Kunststofopassing B.V.
Nijverheidsweg 37
P.O.Box 131
3340 AC Hendrik-Ido-Ambacht
The Netherlands